

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

MarFlex[®] HHM TR-257

Low Density Linear Polyethylene

This LDPE is tailored for applications that require:

- Good processibility
- Good melt strength
- Good drawdown
- Good strength
- Satin finish
- Good MD & TD shrinkage

Typical blown film applications include:

- Pallet shrink
- Heavy duty bags
- Consumer & institutional shrink film
- General purpose packaging

Nominal Resin Properties	English	SI	Method
Density	---	0.923 g/cm ³	ASTM D1505
Melt Index, 190C/2.16Kg	---	0.2 g/10min	ASTM D1238
Process Aid	None	None	---
Antiblock	None	None	---
Slip	None	None	---

Nominal Film Properties at 1 mil ¹	English	SI	Method
Haze	33 %	33 %	ASTM D1003
Gloss, 60°	46	46	ASTM D2457
COF	0.35	0.35	ASTM D1894
Dart	---	46 g/mil	ASTM D1709
Elmendorf Tear MD/TD	---	12/945 g/mil	ASTM D1922
Tensile Strength at Break MD/TD	10500/4300 psi	72/30 MPa	ASTM D882
Tensile Strength Elongation at Break MD/TD	380/800 %	380/800 %	ASTM D882
1% Secant Modulus MD/TD	53000/73000 psi	365/500 MPa	ASTM D882

1. Seated bubble, 2.5 BUR, 80 mil die gap, 8" die, 250 lb/hr, 400F melt temp.

Revision Date January, 2008

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

MarFlex[®] HHM TR-257

Low Density Linear Polyethylene

Nominal Film Properties at 1 mil ¹	English	SI	Method
Haze	36 %	36 %	ASTM D1003
Gloss, 60°	40	40	ASTM D2457
COF	0.35	0.35	ASTM D1894
Dart	---	140 g/mil	ASTM D1709
Elmendorf Tear MD/TD	---	30/400 g/mil	D1709
Tensile Strength at Break MD/TD	8800/6600 psi	61/46 MPa	ASTM D882
Tensile Strength Elongation at Break MD/TD	460/650 %	460/650 %	ASTM D882
1% Secant Modulus MD/TD	53000/58000 psi	365/400 MPa	ASTM D882

1. High Stalk, 4:1 BUR, 40 mil die gap. 8" die, 250 lb/hr, 430F melt temp.

Revision Date January, 2008

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.